

Typical Physical Properties / Typische Physikalische Eigenschaften

Product Code Produkt Code	Product Description Produkt Beschreibung	CI	Pigment %	S.g. Dichte	Weather fastness Wetterbeständigkeit		Light fastness Lichtechtheit		Heat Stability Hitze-Beständigkeit	Solvent Fastness Lösemittelbeständigkeit
					Fulltone Vollton	Reduction Aufhellung 1/25	Fulltone Vollton	Reduction Aufhellung 1/25		
888-0018 KX	Titanium White	PW 6	54	2.015	5	5	8	8	> 200°C	5
888-0422 V	Quinacridone Magenta	PR 122	11	1.250	3-4d	2-3	7d	6	200°C	4-5
888-0836 R	Organic Red	PV 19 / PR 122	14	1.345	3-4d/ 3-4d	3-4/2-3	6-7d / 7d	7 / 6	260°C / 200°C	5 / 4-5
888-1045 F	Red Iron Oxide	PR 101	59	2.040	5	5	8	8	> 200°C	5
888-1572 I	Brown Iron Oxide	PY 42 / PR 101 / PBk 7	40	1.720	5	5	8	8	200°C	5
888-1810 C	Yellow Iron Oxide	PY 42	55	1.830	5	5	8	8	180°C	5
888-2009 L	Raw Umber	P Brn 7	27	1.525	5	5	8	8	200°C	n/a
888-2040 T	Medium Yellow	PY 65/ PY 74	39	1.260	4-5/ 4-5	4/ 3-4	6-7/ 7-8	6-7/ 7	150°C/ 150°C	/ 3-4
888-2551 AXX	Organic Yellow	PY 74 / PY 3	20	1.380	4-5 / 4-5	3-4 / 3	7-8 / 7-8	7 / 6-7	150°C / 150°C	3-4 / 2
888-5511 D	Phthalo Green	PG 7	11	1.445	5	5	8	8	200°C	5
888-7214 E	Phthalo Blue	PB 15:2	5	1.385	5	5	8	8	200°C	5
888-9907 B	Lamp Black	PBk 7	8	1.355	5	5	8	8	> 200°C	5

02-04 rev00

All data obtained directly from pigment suppliers, individual testing is recommended / Alle oben aufgeführten Daten wurden von den entsprechenden Pigmentherstellern übernommen.
 Light fastness is measured on scale 1 to 8, where 1=severe change and 8=no change / Lichtechtheit ist bestimmt nach dem Blaumassstab, wobei 1 schlechtestes und 8 bester Wert ist.
 Weather and solvent fastness (tests performed with several commonly used solvents) are measured on scale 1 to 5, where 1=severe change and 5=no change. / Wetter- und Lösemittelbeständigkeit (Tests durchgeführt mit allgemein eingesetzten Lösemitteln) sind getestet auf eine Skala von 1 bis 5, wobei 1 schlecht und 5 gut ist.
 "d" = color turns darker / "d" = Farbton wird dunkler.
 "n/a" = not available from pigment supplier / keine Angabe vom Pigmenthersteller verfügbar

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used

